

WISA®-Spruce Special

WISA-Spruce Special is a smooth, strong, structural multipurpose plywood panel with a superior surface quality. The panel is light in weight yet strong and rigid, typically used in load bearing structures. The refined look and smooth surface makes it suitable for other uses as well including shop fittings, joinery, furniture and DIY use. The panel is ideal for projects demanding outstanding environmental performance and consistent high quality.

Bonding

Weather resistant glueing according to EN 314-2/class 3 Exterior. WISA-Spruce Special fulfills the requirements of EN 13986 E1 low formaldehyde emission class.

On request deliveries according to TSCA Title IV / CARB Phase II / JAS Four Stars.

Surface

Face: Grade G (solid surface with no open defects)

Reverse: Grade III (comply with standard EN 635-3)

Machining

Edge machinings available on request.

Thicknesses and weights

Nominal thickness (mm)	Number of plies	Thickness (mm)		Weight (kg/m ²) abt
		Min	Max	
9	3	8.8	9.5	4.1
12	5	11.5	12.5	5.7
15	5	14.3	15.3	7.0
18	7	17.1	18.1	8.1
21	7	20.0	20.9	9.4
24	9	22.9	23.7	10.7
27	9	25.2	26.8	12.1
30	11	28.1	29.9	13.9

Sizes and thicknesses relating to moisture content 8 - 12 %.
Thicknesses and tolerances fulfil the EN 315 requirements.



For PEFC™ products, visit www.pefc.org



The mark of responsible forestry
For FSC® products, visit www.fsc.org





Panel sizes

Standard sizes Length from 2400 to 2500 mm
 Length 2700 mm
 Width from 1200 to 1250 mm
 Tongued and grooved 2400/2440 x 600/1200 mm

Size tolerances < 1000 mm ±1 mm
 1000 - 2000 mm ±2 mm
 > 2000 mm ±3 mm

Squareness tolerance ±1 mm / 1000 mm

Strength values and technical properties

WISA-Spruce Special is CE marked according to AVCP System 2+ for structural use.

For all detailed technical values, please see product-specific DoP (Declaration of Performance) on www.wisaplywood.com/dop.

Storing instructions

Panels should be stored in a covered and dry place and to be kept flatwise.

Installation instructions

The panels can have dimensional changes due to changes in the air humidity. The square edge of the panel should have 1 mm/m expansion gap between panels. For more information on handling, please see Guide to Good Practice on www.wisaplywood.com.

Additional information

Wood being a living material, every panel is unique. Thus a photograph or a sample piece cannot represent all the panels, as regards colours, shades, graining, knots etc.

For further information of installation, maintenance, disposal, environmental matters etc. please see www.wisaplywood.com or contact your supplier or UPM.



UPM Plywood

www.wisaplywood.com
www.upm.com

UPM policy is one of continuous development. We reserve the right to amend specifications without notice or obligation.