

# WISA®-Trans Mk2

WISA-Trans Mk2 is a slip-resistant plywood panel for demanding flooring applications in transport and construction. The panel is made of birch veneers glued together in special-oriented or cross-banded constructions. The product is intended for use as flooring in trucks, trailers and railway wagons but also for demanding building applications such as warehouse floors and loading platforms. The uniquely patterned coating is especially wear-resistant, which helps prolong the service life of vehicles.

#### Base panel

Birch plywood made solely from birch (hardwood) veneers.

#### **Bonding**

Weather resistant gluing according to EN 314-2 / class 3.

#### **Construction**

Special oriented construction. Standard constructions available on request.

#### **Surfaces**

Face: Phenolic resin impregnated multi-layer laminate with high friction pattern.

Reverse: Phenolic resin coating with WISA-Trans imprint.

Colour: Dark brown

#### **Edge protection**

Acryl-based paint.

## Machining

Edge- and CNC machinings available on request.

## Thicknesses and weights

Nominal thickness	Number of plies	Thickne	Weight	
(mm)		Min	Max	$(kg/m^2)$
18	13	17.1	18.1	12.2
21	15	20.0	20.9	14.3
22	16	21.3	22.3	15.3
24	17	22.9	23.7	16.3
25	18	24.1	25.1	17.4
27	19	25.2	26.8	18.4
28	20	26.9	27.9	19.4
30	21	28.1	29.9	20.4
31	22	29.6	31.2	21.5
35	25	33.5	36.1	23.8

**UPM**PLYWOOD









For FSC® products, visit www.fsc.org



## **Panel sizes**

Standard dimensions:  $1200/1220/1250/1500/1525 \times 2400/2440/2500/3000/3050 \text{ mm}$ 

Other sizes on request. The largest size available  $1525 \times 3500$  mm.

Size tolerances: < 1000 mm  $\pm 1 \text{ mm}$ 

1000-2000 mm  $\pm 2 \text{ mm}$  2000-3500 mm  $\pm 3 \text{ mm}$ 

Squareness tolerance:  $\pm 1 \text{ mm} / 1000 \text{ mm}$ 

# Properties of panel surface

Face: Taber abrasion value (DIN 53799) 3700 rounds Rolling test value (SS 923508) 8000 ±35 % cycles

Improved water resistance through coatings on the face and the reverse.

## **Strength values** (according to ISO 1496-1)


With special oriented construction

Span		300 mm		400 mm		500 mm	
Thic	kness n	P (kg)	d (mm)	P (kg)	d (mm)	P (kg)	d (mm)
18	13	1500	7.1	1200	10.7	1000	14.1
21	15	2000	6.4	1600	9.4	1300	11.9
22	16	2300	6.0	1900	9.2	1700	12.9
24	17	2600	5.9	2200	9.0	1900	12.1
25	18	2900	5.6	2500	8.7	2100	11.3
27	19	3200	5.4	2800	8.4	2400	11.1
28	20	3600	5.2	3000	7.7	2700	10.7
30	21	3900	5.0	3300	7.5	2900	10.1
31	22	4100	4.7	3500	7.0	3100	9.5
35	25	5200	4.4	4400	6.4	3900	8.5

n = number of plies

For specific loading details please contact your supplier.

## Installation



For further information on installation, maintenance, disposal, environmental matters etc. please visit www.wisaplywood.com.



P = ultimate wheel load (no safety factor applied)

d = deflection with ultimate wheel load

Wheel contact area  $80 \times 180$  mm (ISO 1496).

All panel edges should be supported