

## DECLARATION OF PERFORMANCE, UPM PLYWOOD No. UPM022CPR

- 1. Unique identification code of the product-type: Structural birch plywood, uncoated, 12–30 mm
- Intended uses:
   For internal use as a structural component in dry conditions, EN 636-1
   For protected external use as a structural component in humid conditions, EN 636-2
- 3. Manufacturer: WISA® UPM Plywood Oy P.O. Box 203 FI-15141 Lahti, Finland www.wisaplywood.com
- 5. System of AVCP: AVCP system 2+
- 6a. Harmonised standard: EN 13986:2004 + A1:2015

Notified body:

Inspecta Sertifiointi Oy No. 0416 has performed the initial inspection of the manufacturing plant and a factory production control and continuous surveillance, assessment and evaluation of factory production control and issued the certificates of conformity of the factory production control 0416-CPR-7108 (Joensuu), 0416-CPR-7109 (Jyväskylä), 0416-CPR-7110 (Pellos), 0416-CPR-7111 (Savonlinna), 0416-CPR-7112 (Chudovo), 0416-CPR-7113 (Otepää).

UPM Plywood Oy

Niemenkatu 16 P.O. Box 203 FI-15141 Lahti Finland Tel. +358 204 15 113 Fax +358 204 15 112 www.wisaplywood.com Domicile Helsinki Business Identity Code 183 9206-5



## 7. Declared performance:

Essential characteristics	Performance	Harmonised standard		
Point load strength and stiffness	NPD			
Racking resistance	Calculation according to EN 1995-1-1			
Impact resistance	NPD			
Water veneur permechility u	Wet 90, dry 220			
Water vapour permeability µ	Mean density 680 kg/m <sup>3</sup>			
Release of formaldehyde	E1	EN 13986:2004+A1:2015		
Content of pentachlorophenol (PCP)	≤ 5 ppm			
Airborne sound insulation	NPD			
Sound absorption $\alpha$	0,10/0,30			
Thermal conductivity $\lambda$	0,17 W/mK			
Embedment strength	Calculation according to EN 1995-1-1			
Air permeability	NPD			
Bonding quality (acc. to EN 314-2)	Class 3			
Biological durability	Use class 2			

Reaction to fire								
End use condition (6)	Minimum thickness (mm)	Class <sup>(7)</sup> (excluding floorings)	Class <sup>(8)</sup> (floorings)					
Without an air gap behind the wood-based panel <sup>(1), (2), (5)</sup>	12	D-s2, d0	D <sub>fl</sub> -s1					
With a closed or an open air gap not more than 22 mm behind the wood-based panel $^{\rm (3),\ (5)}$	12	D-s2, d2	_					
With a closed air gap behind the wood-based panel $^{\rm (4),(5)}$	15	D-s2, d1	D <sub>fl</sub> -s1					
With an open air gap behind the wood-based panel $^{\rm (4),(5)}$	18	D-s2, d0	D <sub>fl</sub> -s1					

(1) Mounted without an air gap directly against class A1 or A2-s1, d0 products with minimum density 10kg/m3 or at least class D-s2, d2.
(2) A substrate of cellulose insulation material of at least class E may be included if mounted directly against the wood-based panel, but not for floorings.
(3) Mounted with an air gap behind. The reverse face of the cavity shall be at least class A2-s1, d0 products with minimum density 10 kg/m3.
(4) Mounted with an air gap behind. The reverse face of the cavity shall be at least class D-s2, d2 products with minimum density 400 kg/m3.
(5) Veneered, phenol- and melamine-faced panels are included for class excl. floorings.
(6) A vapour barrier with a thickness up to 0,4 mm and a mass up to 200 g/m2 can be mounted in between the wood-based panel and a substrate if there are no air gaps in between.
(7) Class as provided for in Table 1 of the Annex to Decision 2000/147/EC.
(8) Class as provided for in Table 2 of the Annex to Decision 2000/147/EC.



Nominal thickness		12	15	18	21	24	27	30	
Number of plies		9	11	13	15	17	19	21	
Essential characteristics		Performance							
Characteristic bending strength N/mm <sup>2</sup>	f <sub>m ∥</sub>	59,0	55,5	52,9	50,9	49,2	47,9	46,8	Harmonised standard EN 13986:2004+A1:2015
	f <sub>m_l_</sub>	18,9	21,8	23,9	25,4	26,5	27,4	28,1	
Characteristic compression strength N/mm <sup>2</sup>	f <sub>c ∥</sub>	33,8	32,3	31,3	30,6	30,0	29,6	29,3	
	f <sub>c_L</sub>	18,2	19,7	20,7	21,4	22,0	22,4	22,8	
Characteristic tension strength	$f_{t\parallel}$	48,8	46,6	45,2	44,1	43,3	42,7	42,2	
	$f_{t\_L}$	26,3	28,4	29,8	30,9	31,7	32,3	32,8	
Mean MOE in	E <sub>m∥</sub>	14749	13886	13228	12715	12305	11970	11692	
bending N/mm <sup>2</sup>	E <sub>m_l_</sub>	2751	3614	4272	4785	5195	5530	5808	
Mean MOE in compression and tension N/mm <sup>2</sup>	E <sub>t,c ∥</sub>	11375	10878	10540	10294	10108	9962	9844	1398
	$E_{t,c\_l\_}$	6125	6622	6960	7206	7392	7538	7656	d EN
Char. panel shear	f <sub>v ∥</sub>	9,5		9,5			dar		
N/mm²	$f_{v\_l\_}$	9,5		9,5			itan		
Char. Planar	f <sub>r∥</sub>	2,7	2,8	2,7	2,8	2,7	2,7	2,7	nised st
shear N/mm <sup>2</sup>	$f_{r\_l\_}$	1,8	1,8	2,0	2,0	2,1	2,1	2,2	
Mean MOR in panel shear N/mm²	Gv∥	620		620			Irmoi		
	G <sub>v_l</sub>	620			620			На	
Mean MOR in planar shear N/mm²	Gr∥	222	219	217	215	214	213	213	
	$G_{r\_L}$	119	138	150	158	164	168	172	
Strength and stiffness under point load		NPD							
Impact resistance	·								
kmod and kdef values according to EN 1995-1-1									

The performance of the product identified above is in conformity with the set of declared performances. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

Lahti, Finland, November 5th, 2018

Sikka almikuukka

Sirkku Salmikuukka, Product Manager UPM Plywood