



DECLARATION OF PERFORMANCE, UPM PLYWOOD

No. UPM001CPR

1. Unique identification code of the product-type:
Structural spruce plywood, uncoated or coated, 9–50 mm
2. Intended uses:
For internal use as a structural component in dry conditions, EN 636-1
For protected external use as a structural component in humid conditions, EN 636-2
For external use as a structural component with coating and edge sealing, EN 636-3
3. Manufacturer:
WISA®
UPM Plywood Oy
Askonkatu 9 C
15100 Lahti, Finland
www.wisaplywood.com
5. System of AVCP:
AVCP system 2+
- 6a. Harmonized standard:
EN 13986:2004 + A1:2015

Notified body:

KIWA Sertifiointi Oy No. 0416 has performed the initial inspection of the manufacturing plant and a factory production control and continuous surveillance, assessment and evaluation of factory production control and issued the certificate of conformity of the factory production control 0416-CPR-7110.

7. Declared performance:

Essential characteristics	Performance	Harmonised standard
Point load strength and stiffness	NPD	EN 13986:2004+A1:2015
Racking resistance	Calculation according to EN 1995-1-1 9mm $\rho_k = 405 \text{ kg/m}^3$ $\geq 12\text{mm } \rho_k = 420 \text{ kg/m}^3$	
Impact resistance	NPD	
Water vapour permeability μ	Wet 66, dry 190 (uncoated)	
	Mean density 460 kg/m^3	
Release of formaldehyde	E1 And Compliant with Commission Regulation (EU) 2023/1464	
Content of pentachlorophenol (PCP)	$\leq 5 \text{ ppm}$	
Airborne sound insulation	NPD	
Sound absorption α	0,10/0,30	
Thermal conductivity λ	0,13 W/mK	
Embedment strength	Calculation according to EN 1995-1-1	
Air permeability	NPD	
Bonding quality (acc. to EN 314-2)	Class 3	
Biological durability	Use class 2 (uncoated)	
	Use class 3 (coated and edge sealed)	

Reaction to fire EN 13986:2004+A1:2015			
End use condition ⁽⁶⁾	Minimum thickness (mm)	Class (excluding floorings)	Class (floorings)
Without an air gap behind the wood-based panel ⁽⁵⁾	9	D-s2, d0	D _{fl} -s1
With a closed or an open air gap not more than 22 mm behind the wood-based panel ⁽⁵⁾	9	D-s2, d2	-
With a closed air gap behind the wood-based panel ⁽⁵⁾	15	D-s2, d1	D _{fl} -s1
With an open air gap behind the wood-based panel ⁽⁵⁾	18	D-s2, d0	D _{fl} -s1

⁽⁵⁾ Veneered, phenol- and melamine-faced panels are included for class excl. floorings.

⁽⁶⁾ A vapour barrier with a thickness up to 0,4 mm and a mass up to 200 g/m² can be mounted in between the wood-based panel and a substrate if there are no air gaps in between.

Nominal thickness		9	12	15	18	21	24	27	30	40	50
Number of plies		3	5	5	7	7	9	9	11	13	17
Essential characteristics		Performance									
Characteristic bending strength N/mm ²	$f_{m }$	28,7	22,8	23,0	20,4	18,9	19,4	19,3	18,7	16,8	15,6
	$f_{m\perp}$	3,8	11,4	11,2	13,0	14,3	13,1	13,8	13,3	14,9	15,9
Characteristic compression strength N/mm ²	$f_{c }$	19,3	17,4	17,5	16,7	16,0	17,0	15,5	17,2	15,5	14,7
	$f_{c\perp}$	10,7	12,6	12,5	13,3	14,0	13,0	14,5	12,8	14,5	15,3
Characteristic tension strength N/mm ²	$f_{t }$	11,6	10,5	10,5	10,0	9,6	10,2	9,3	10,3	9,3	8,8
	$f_{t\perp}$	6,4	7,5	7,5	8,0	8,4	7,8	8,7	7,7	8,7	9,2
Mean MOE in bending N/mm ²	$E_{m }$	10050	9123	9201	8170	7547	7751	7702	7479	6723	6227
	$E_{m\perp}$	539	2876	2799	3830	4453	4249	4298	4521	5277	5773
Mean MOE in compression and tension N/mm ²	$E_{t,c }$	7733	6968	7013	6682	6408	6800	6182	6868	6211	5880
	$E_{t,c\perp}$	4267	5032	4987	5318	5592	5200	5818	5132	5789	6120
Char. panel shear N/mm ²	$f_{v }$	3,5	3,5		3,5						
	$f_{v\perp}$	3,5	3,5		3,5						
Char. Planar shear N/mm ²	$f_{r }$	1	1		1						
	$f_{r\perp}$	NPD	0,6		0,8						
Mean MOR in panel shear N/mm ²	$G_{v }$	350	350		350						
	$G_{v\perp}$	350	350		350						
Mean MOR in planar shear N/mm ²	$G_{r }$	45	50		50						
	$G_{r\perp}$	NPD	30		40						
k _{mod} and k _{def} values according to EN 1995-1-1											

Harmonised standard EN 13986:2004+A1:2015

The performance of the product identified above is in conformity with the set of declared performances. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

Lahti, Finland, January 1st, 2026



Riku Härkönen, Product Manager
UPM Plywood Oy