

DECLARATION OF CONFORMITY, UPM PLYWOOD

No. UPM025CPR

1. Unique identification code of the product-type:
Structural birch plywood, Multi-coated, 6,5–30 mm
2. Intended uses:
For internal use as a structural component in dry conditions, EN 636-1
For protected external use as a structural component in humid conditions, EN 636-2
For external use as a structural component with coating and edge sealing, EN 636-3
3. Manufacturer:
WISA®
UPM Plywood Oy
P.O. Box 203
FI-15141 Lahti, Finland
www.wisaplywood.com
4. Authorized representative
UPM Wood Material (UK) Limited
Rutherford House, First Floor, Warrington Road, Birchwood
Warrington, Cheshire
WA3 6ZH
United Kingdom
5. System of AVCP:
AVCP system 2+
- 6a. Harmonised standard:
EN 13986:2004 + A1:2015

Notified body:

CATG Ltd. No. 1245 has performed the initial inspection of the manufacturing plant and a factory production control and continuous surveillance, assessment and evaluation of factory production control and issued the certificates of conformity of the factory production control 1245-CPR-5001 (Savonlinna), 1245-CPR-5002 (Joensuu), 1245-CPR-5003 (Pellos), 1245-CPR-5005 (Otepää).

7. Declared performance:

Essential characteristics	Performance		Harmonised standard
Reaction to fire	End use condition: any	F	EN 13986:2004+A1:2015
Point load strength and stiffness	NPD		
Racking resistance	Calculation according to EN 1995-1-1		
Impact resistance	NPD		
Water vapour permeability μ	NPD		
	Mean density 680 kg/m ³		
Release of formaldehyde	E1		
Content of pentachlorophenol (PCP)	≤ 5 ppm		
Airborne sound insulation	NPD		
Sound absorption α	0,10/0,30		
Thermal conductivity λ	0,17 W/mK		
Embedment strength	Calculation according to EN 1995-1-1		
Air permeability	NPD		
Bonding quality (acc. to EN 314-2)	Class 3		
Biological durability	Use class 3		

Nominal thickness		6,5	9	12	15	18	21	24	27	30	Harmonised standard EN 13986:2004+A1:2015
Number of plies		5	7	9	11	13	15	17	19	21	
Essential characteristics											
Characteristic bending strength N/mm ²	f _m	44,6	46,4	42,9	41,3	40,2	39,4	38,9	38,4	38,1	
	f _{m⊥}	18,5	27,4	33,2	33,8	34,1	34,3	34,4	34,5	34,6	
Characteristic compression strength N/mm ²	f _c	29,3	28,3	27,7	27,4	27,2	27,0	26,9	26,8	26,7	
	f _{c⊥}	22,8	23,7	24,3	24,6	24,8	25,0	25,1	25,2	25,3	
Characteristic tension strength N/mm ²	f _t	42,2	40,8	40,0	39,5	39,2	39,0	38,8	38,7	38,5	
	f _{t⊥}	32,8	34,2	35,0	35,5	35,8	36,0	36,2	36,3	36,5	
Mean MOE in bending N/mm ²	E _m	11400	10850	10719	10316	10048	9858	9717	9607	9519	
	E _{m⊥}	4270	6060	6781	7184	7452	7642	7783	7893	7981	
Mean MOE in compression and tension N/mm ²	E _{t,c}	9844	9511	9333	9223	9148	9093	9052	9019	8993	
	E _{t,c⊥}	7656	7989	8167	8277	8352	8407	8448	8481	8507	
Char. panel shear N/mm ²	f _v	9,5	9,5	9,5							
	f _{v⊥}	9,5	9,5	9,5							
Char. Planar shear N/mm ²	f _r	3,2	2,6	2,6							
	f _{r⊥}	1,8	2,4	2,4							
Mean MOR in panel shear N/mm ²	G _v	620	620	620							
	G _{v⊥}	620	620	620							
Mean MOR in planar shear N/mm ²	G _r	170	205	205							
	G _{r⊥}	120	160	180							
Strength and stiffness under point load		NPD									
Impact resistance		NPD									
K _{mod} and K _{def} values according to EN 1995-1-1											

The performance of the product identified above is in conformity with the set of declared performances. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by:

Lahti, Finland, January 1st, 2023



Timo Lindroos, Product Manager
UPM Plywood